

CAUTION Keep out of reach of children
Read safety directions before opening

MASONRY SEALER

HORIZONTAL AND VERTICAL MASONRY SEALING COMPOUND

CLEAR RED BLACK YELLOW GREY

It is recommended that on some dense surfaces that the first coat of CYNDAN* MASONRY SEALER (CLEAR) should be prediluted with XYLENE at a mix rate of 1 part XYLENE to 3 parts CYNDAN* MASONRY SEALER. This allows for better penetration and adhesion if this premix is required, please order the Xylene from your Cyndan Representative. For the coloured MASONRY SEALER Xylene CAN NOT be used as the prediluting solvent. To predilute COLOURED CYNDAN* MASONRY SEALER please order "Coloured Masonry Sealer Diluting Solvent" from your Cyndan Representative.

DIRECTIONS:

One litre of CYNDAN* MASONRY SEALER will approximately cover 6 sq. metres (60 sq. ft.). Spray or brush the CYNDAN* MASONRY SEALER over the surface ensuring the entire area is covered. Drying time will vary with the conditions of the day. 20 minutes is normally adequate. This single coat will seal the surface. The surface to be covered should be dry before application.

These surfaces first must be cleaned thoroughly, ensuring all grease, oil, dirt and dust are removed. CYNDAN'S* CONCRETE WASH will achieve the best results for this cleaning operation. After cleaning the floor should be left to thoroughly dry. Apply the CYNDAN* MASONRY SEALER as described above.

To gain a finish which has some lustre 2 - 3 coats should be applied. One coat however will penetrate and seal the surface.

NOTE: As with all coatings the CYNDAN* range is sensitive to silicone residues. In addition, the coatings are only as good as the surface that they are applied to. Surface preparation is critical. To detect silicone residue or other contaminants, please ask your CYNDAN* representative to do a test piece for you. To remove silicone residues, if found, use Prepsol.

SAFETY: Avoid contact with eyes.

FIRST AID: If swallowed, do NOT induce vomiting, give a glass of water and seek medical attention. Contact the Poisons Information Centre (13 11 26 Australia; 0800 764 766 New Zealand). If in eyes, hold eyelids open and flush with water for at least 15 minutes.

Batch #:

* Trademark



9 343310 005718

Cyndan Chemicals 1/7 Jubilee Avenue Warriewood NSW 2102 AUSTRALIA ph +61 2 9998 5688 www.cyndan.com.au